



## E&J TECHNOLOGY GROUP CO., LTD

# Ni-MH Low Self-Discharge Battery Specification

Model Number: EJ44AAA800S

Doc No: <u>SPE-NH-0130</u>

Version: 01

Date: <u>2012-03-16</u>

Prepared	Checked	Approved
Sara	Jess	John

## **E&J TECHNOLOGY GROUP CO., LTD**

ADD: Building 13, 403 gong village industry, Longhua, Shenzhen, China

Tel:+86-755-29064219 Fax:+86-755-22635063

Website: http//www.ejbattery.com E-mail:sales@ejtechgroup.com



## 1、Scope

This specification is suitable for the performance of the E&J Ni-MH Low Self rechargeable battery.

#### 2. Model

EJ44AAA800S

## 3.Appearance

There shall be no such defects as deformation, flaw, stain, discoloration or electrolyte leakage.

## 4. Nominal specification

Description			Specification	
Model			EJ44AAA800S	
Size			AAA	
	Diameter (mm)		10.5+0/-0.7	
Dimensions	Н	leight (mm)	44.0+0/-1.5	
	,	Weight (g)	Approx. 11.0 g	
Nominal Voltage (V)		e (V)	1.2	
Nominal capacity (mAh)		(mAh)	800	
Internal	Internal Impedance (mΩ)		≤45	
Discharge Cut-off Voltage		Voltage	1.0V	
	Ch	Standard	0°C to 40°C	
	arge	Fast	10℃ to 40℃	
		Discharge	-10℃ to 50℃	
temperature	Stor	<1 year	-10℃ to 30℃	
	age	<3 months	-10℃ to 40℃	
		The relative humidity should keep with in 65±20%		

#### 5. Characteristics

Unless otherwise specified, test: should be done within one month of delivery under the following conditions:

♦ Ambient temperature 20±5°C

♦ Relative humidity 65±20%

◆ Atmospheric pressure 960±100mbar

## **Professional NI-MH Battery manufacturer**

Test item		Condition	Specification
1. Charge	Standard	Charge at 0.1C for 16 hours	0℃ to 40℃
	Fast	Charge at 0.5C to -△V=0-5mV	10℃ to 40℃
	Trickle	(0.03C)-(0.05C)	0℃ to 40℃
2. Discharge		At 0.2C to 1.0V	
3.Discharge cut-o	off voltage		1.0V
4.Capacity (mAh)	Minimum	Standard charge/discharge	750
	Typical	Standard charge/discharge	800
5. Internal resista	ance/	After fully charge,rest 1 hour, measured at 1000Hz	≤45mΩ
6.Hight Rate Discharge		Standard charge 1hour rest Before Discharge by 0.5C to 1.0V	≥108minutes
		Standard charge 1hour rest Before Discharge by 1C to 1.0V	≥48minutes
7.Overcharge		0.1C charger 28 days,	No leakage
8.Charge Retenti	on	The charged battery is stored for 12months at 20 °C . And the discharge time is measured at standard discharge	Capacity≥75%

## **Professional NI-MH Battery manufacturer**

Cycle time	Charge	Rest	Discharge	
1	0.1C for 16h	0	0.25C for 2h20min	
2~48	0.25C for 3h10min	0	0.25C for 2h20min	
49	0.25C for 3h10min	0	0.2C to 1.0V	
50	0.1C for 16h	1~4h	0.2C to 1.0V	
9.Leakag	e Test	Standard 14days	charge stand for	No leakage
10. High	temperature test		0℃、50℃、60℃ for en charge/discharge	No leakage
11.Low to	emperature test	Store at (	)℃ for 2 hours then charge	No leakage
12.Short circuit test		Short circuit after fully charge		No explode
13. Drop test			n the concrete from 1 er fully charged	No leakage No short-circuit

#### **Professional NI-MH Battery manufacturer**

#### 6. Cautions in use

To ensure proper use of the battery please read the manual carefully before using it.

#### Handling

Do not expose to, dispose of the battery in fire.

Do not put the battery in a charger or equipment with wrong terminals connected.

Avoid shorting the battery.

Avoid excessive physical shock or vibration.

Do not disassemble or deform the battery.

Do not immerse in water.

Do not use the battery mixed with other different make, type, or model batteries.

Keep out of the reach of children

#### Storage

Cycle(charge and discharge)the battery every 6-9month to maintain cell/battery performance, When being stored for an extended period of time

Store the battery in a cool, dry and well-ventilated area.

### Disposal

Regulations vary for different countries.


Dispose of in accordance with local regulations.

#### 7. Note


Any other items which are not covered in this specification shall be agreed by both parties.




## Appendix:Battery performace curve




Project	Description	Dimension (mm)
D1	Diameter 1	Max 4.0
D	Diameter	10.5 +0 -0.7
H1	Height 1	≥1.2
Н	Height	44.5 +0 -1.5





## DISCHARGE CHARACTERISTICS



DISCHARGE CHARACTERISTICS AT DIFFERENT TEMPERATURE

